

# **NEW PORTRAITS RANGE**

Product Name: **PORTRAITS - VARIOUS COLOUR/FINISHES** 

Product Identifier: Refer to tile name and product code on paperwork/packaging

Product Description: A glazed porcelain tile and a water absorption rate of less than 0.50%.

Country Of Origin: Italy

### **Building Code Obligations**

Code Clauses: <u>B2 – Durability</u> B2.3.1 <u>C3 – Fire affecting areas beyond the</u> <u>source</u> D1 – Access routes D1.3.3 <u>E3 – Internal moisture</u> E3.3.2, 3.3.3, 3.3.4 <u>G3 – Food preparation and prevention of</u> <u>contamination</u> G3.3.2 <u>G6 – Airborne and Impact sound</u> G6.3.1



Note - this building product is not subject to a warning/ban under section 26 of the Building Act 2004

Manufacturer Details: European Ceramics Approved BPIR COMPLIANT

Scope	Use
B2 Durability	See below suitability table
C3 Fire	The Building Code relating to fire ratings regulation & standards become mandatory from April 2013, establishing the list of products belonging to Classes A 'No Contribution to Fire' provided for in Decision 94/611/EC implementing Article 20 of Council Directive 89/106/EEC.
D1 Access Routes	Refer to slip resistance documentation for all Access routes classifications D1/AS1 for above range.
E3 Internal Moisture	Under E3 Tiles installed over a waterproof membrane using a nonporous grouting system, are an acceptable solution.
G3 Food Preparation & Prevention from Contamination	As an impervious and easy to clean surface, this range complies.
G6 Airborne & Impact Sound	If required, tiles can form part of an acoustic system to comply with IIC & STC in conjunction with an approved third-party system.

Suitability *	Residential	Light Commercial	Commercial
Indoor Floor	*	*	*
Indoor Walls	*	*	*
Outdoor Cladding	*	*	*
Frost Resistant	*	*	*
Swimming Pool Submerged	*	*	*
Swimming Pool Surround	*	*	*
Paving/External	*	*	*
Over Underfloor Heating	*	*	*
Kitchen wall	*	*	*
Within 1.5m of a Plumbing Fixture or Fitting	*	*	*

Manufacturer Details: European Ceramics Approved BPIR COMPLIANT

## **Building Code References**

#### **B2** – Durability

Compliance with B2 Durability is about providing evidence that the product will meet the relevant durability life in the context of the environment in which it will be located.

The building code sets out the framework for establishing the relevant durability life of building elements based on a number of criteria. B2/AS1 provides a decision tree to establish the relevant durability for common building materials in different circumstances.

Having determined the durability life of the product, the next step is to determine if the product, when exposed to the environment, will continue to perform for the relevant period. A key tool which a product supplier can consider in claiming compliance is limiting the environment in which the product will be exposed to (e.g. a ferrous material used in an indoor environment will last longer than it would when exposed to salt spray — in this example it would be appropriate for the supplier to condition the compliance information to use only in indoor environments).

#### C3 – Fire affecting areas beyond the source

C3 Fire affecting areas beyond the fire source is primarily about ensuring that fire does not spread from a fire in the building (in both vertically and horizontally) and from an adjacent building.

The prime product attribute used is the fire resistance rating (FRR) methodology. In most cases a product is combined with other products to achieve a FRR (e.g. an external wall fire rating may be formed by the combination of the external cladding, thermal insulation and the internal lining.

C/AS1 and C/AS2 set out performance criteria for buildings and in particular the FRR requirements for various types of buildings and parts of buildings. Appendix C of C/AS2 sets out test methods for the building elements involved in spread of fire. Appendix B of C/AS2 sets out performance criteria for sprinkler systems while Appendix A sets out criteria for fire safety systems such as alarms and hydrants.

#### D1 – Access routes

For D1 access routes, in most cases product-related compliance for access routes is slip resistance for floors and the shapes/locations etc of handrails. The Acceptable Solution for access D1/AS1 and NZS 4121:2001 provide good information on compliance for products on access routes.

#### E3 – Internal Moisture

E3 Internal Moisture is about ensuring that moisture created within the building does not lead to mould or create damage to adjacent buildings or structural elements in the building in which it is installed.

Prevention of the creation of mould is a combination of temperature, insulation and ventilation. Prevention of water damaging other building elements is mainly about installation details (i.e. sealing joints) as well as impervious products. E3/AS1 provides some useful design details, albeit without much product material information.

Manufacturer Details: European Ceramics Approved BPIR COMPLIANT

#### G3 – Food preparation and prevention of contamination

G3 Food preparation and prevention from contamination for a product (such as a kitchen bench) is mainly associated with being easily cleaned and impervious. G3/AS1 provides some general design details for food preparation areas but has no referenced product standards, although the document does state some acceptable materials used for surfaces. Compliance with G3/AS1 is not mandatory but provides a good benchmark for compliance.

#### G6 – Airborne and Impact Sound

For a product, G6 Airborne and impact sound is generally about systems which are designed to work together to achieve the necessary sound attenuation.

The code itself at G6.3.2 sets a quantifiable performance level: "The Sound Transmission Class of walls, floors and ceilings, shall be no less than 55" and G6.3.2 sets the impact insulation class of floors shall be no less than 55. The Acceptable Solution G6/AS1 sets out the transmission and impact insulation class of common wall systems. G6/VM1 sets out test methodologies where the details do not match those of G6/AS1.

Formato - Size - Format	- Формат	Scatola - Box - Boîte	е - Karton - Коробка		Pallet - Pallette - Na	лета	
CM	INCHES	PZ	MQ	KG	SC	MQ	KG
160x320	63"x126"	1	5,12	~78	14	71,68	~1092
120x278	47²/s"x109²/ss"	1	3,3221	~49,56	18	59,798	~892,08
120×120	47²/a"x47²/a"	2	2,85605	~62	20	57,121	~1240
80x80	314/s"x314/s"	2	1,28	~27,36	48	61,44	~1313,28
60x120	23 <sup>s</sup> / <sub>8</sub> "x47 <sup>2</sup> / <sub>8</sub> "	2	1,44	~29,00	35	50,4	~1015
60×60	235/s"x235/s"	4	1,44	~28,00	30	43,20	~840
40x60	15°/s"x23°/s"	4	0,96	~18,64	30	28,80	~559,2
30x60	11º3/16"x235/18"	7	1,26	-24,50	40	50,40	~980
20x60	7 <sup>7</sup> /s"x23 <sup>5</sup> /s"	7	0,84	~16,59	48	40,32	~796,32
10x60	315/16"x235/18"	14	0,84	~16,32	40	33,60	~652,80
60×120 A E X T R A 2 0	23°/="x47²/="	1	0,72	~33,35	35	25,2	~1167,25
60x90 A E X T R A Z O	23°/8"x357/16"	2	1,08	~48,5	24	25,95	~1164
80x80 A E X T R A Z O	314/s"x314/s"	1	0,64	~29,7	42	26,88	~1247,4
60x60 A E X T R A 2 0	23°/#"x23°/#"	2	0,72	~32	30	21,6	~960
60x60 AEXTR 30	235/#"x235/#"	1	0,36	~23,68	40	14,40	~947,20

## **Technical Information**

Manufacturer Details: European Ceramics Approved BPIR COMPLIANT



#### · Tile Performance Data · Caracteristique Technique · Technische Daten · Материал для ваших проектов

Classificazione secondo EN ISO 14411 ISO 13006 annesso G gruppo Bla con Ev <0,5 % · Classification in accordance with EN ISO 14411 ISO 13006 annex G standards Bla with Ev < 0,5% · Classification selon EN ISO 14411 ISO 13006 annexe G groupe Bla avec Ev <0,5% · Klassifizierung gemäß EN ISO 14411 ISO 13006 anlage G Gruppe Bla mit Ev <0,5% · Классификация в соответствии с EN ISO 14411 ISO 13006,приложение G, стандарт Bla, где Ev ≤0,5%

	CARATTERISTICA TECNICA TILE PERFORMANCE DATA CARACTERISTIQUE TECHNIQUE	METODO DI PROVA TESTS METHOD METHODE D'ESSAI TESTMETHODE			VALORE * MEDIO *CAESA *CAESAR* DURC	NR" - AVE HSCHNIT	RAGE "CA TSWERT	ESAR" V * - CPED	ALUE * . HEE 3HA	VALEUR HEHME "		
	TECHNISCHE DATEN TEXHIVHECKAR XAPAKTEPI/CT//KA	МЕТОД ИСПЫТАНИЯ	MATT / G	RIP	A E )	TR	A 2 0				ÆXTRA	0
$\leftarrow^\uparrow$	Dimensione - Size Dimension - Abmessungen - Pazwep	ISO 10545-2	Conforme - In accord Conforme - Erfüllt - C		Conforme - In accordance Conforme - Erfüllt - Coorae	тствует					Conforme - In accordance Conforme - Erfüllt - Cootae	пствует
$\Diamond$	Assorbimento d'acqua* - Water absorption* - Absorption d'eau* - Waseraufnahme* - % Поглощения воды*	ISO 10545-3	s 0,1%		s 0,1%						s 0,1%	
<u>↓</u> ↓ ↑	Resistenza ella flessione* - Banding strength* Risistance à la fiexion* - Biegezugfestigkeit* - Yhpyrocm*	ISO 10545-4	Conforme - In accord Conforme - Erfüllt - C	ance сответствует	Non applicable a plastrelle Not applicable to tiles with a N'est pas applicable aux cam anwendbar bei Flessen mit ei numtok o прочности на pas 2 3000 N	breaking st aeux avec i vor Bruchla	renght		re - Nicht я в отноц	юнии	applicable aux carreaux avec	breaking strenght - N'est pas une charge de rupture - Nicht ser Bruchlest- He применяется
ð?	Sforzo di rottura (S) - Breaking strength Charge de rupture - Bruchlast - Разрушающее усилие	ISO 10545-4	Sps ≈ 7,5 mm S ≈ 1300 N		> 10.000 N						> 21.000 N	
٥	Resistenza all'abrasione profonda* - Deep scratch resistance* - Resistance à l'abrasion profonde* - Widerstand gegen Tieferwerschleiß* - Устойчивость глубоксму истираних*	ISO 10545-6	Conforme - In accord Conforme - Erfüllt - C		Conforme - In accordance Conforme - Erfüllt - Coortee	тствует					Conforme - In accordance Conforme - Erfüllt - Coorse	тствует
₿÷	Coefficiente di dilatazione termica lineare* Thermai linear expansion coefficient* Coefficient de dilatation thermique linéaire* Koefficient de linearen thermischen Dehnung* Koeффициент линейного теплового расширения*	ISO 10545-8	≥7(10°*C')		<u>~</u> 7 (10 ° °C-1)						<u>∞</u> 7 (10+*°C-1)	
	Resistenza agli sbalzi termici* - Termal shock resistance* - Rasistance aux écarts de température* - Temperaturvechsel Bastándigkeit* - Устой-ивость к тепловому перепару*	ISO 10545-9	Resistente - Resistant Résistante - Bestândig	- Стойкий	<b>Resistente</b> - Resistant Résistante - Beständig - Cro	มัคนณี					<b>Resistente</b> - Resistant Résistante - Bestândig - Cπ	મેળ્યો
$\bigcap$	Dilatatione all'umidità* - Expansion in humidity* Dilatationt à l'umidité* - Feuchtigkeitsausdehnung* Расширение в условиях влажности*	ISO 10545-10	s 0,1 (mm/m)		= 0,1 (mm/m)						s 0,1 (mm/m)	
*	Resistenza al gelo* - Frost resistance* - Rèsistance au gel* Frostbeständigkeit* - Морозоустойникость*	ISO 10545-12	Resistente - Resistant Résistante - Bestândig		Resistente - Resistant Résistante - Beständig - Cro	พัฒพิ					Resistente - Resistant Résistante - Bestândig - Cro	મોન્ડમો
\$	Resistenza all'attacco chimico <sup>®</sup> - Resistance to chemical attack <sup>®</sup> - Resistance à l'attaque chimique <sup>®</sup> - Bestăndigkeit gegen Chemikalien <sup>®</sup> Устойчивость к химичеокому водрайствико <sup>®</sup>	ISO 10545-13	Resistente - Resistant Résistante - Bestândig		Resistente - Resistant Résistante - Beständig - Cro	พัฒพิ					Resistente - Resistant Résistante - Bestândig - Cro	iñoiñ
$\downarrow$	Carlos statiços - Static Ioad - Charge statique Statische Last - Crameeoxan earpyoxa	EN 12825			Centro - Centre - Au centra - Mitta - To usempy Centro lato - Sida centre - Au centre latéralement - Mitta Sala - To usempy rpaes Diagonale - Diagonal - En diagonale - Diagonal - En diagonale - Diagonal - En diagonale - Diagonal - En	KN>5,0 KN>4,0	KN>5,0	KN>8,0 KN>6,0	KN>7,0 KN>5,0	KN>5,0 KN>4,0	Au centre laterarement - Mitte Seite - По центру грани	60x60 KN>16,0 KN>11,0 KN>19,0
¥	Classe di carico di rottura*** - Breeking load class*** Classe de charge de ruptura*** - Bruchlastidasse*** Knacc стойности к разрушающей нагрузке***	EN 1339			U11 ***						U25	
ø	Resistenza alle macchie* - Resistance to stains* Résistance eux taches* - Flockenbestă ndigkeit* Устой-ивость k образованию пятен*	ISO 10545-14	Pulibile - Cleanable Nettoyable - Leicht zu Чистящийся	reinigen	Pulibile - Cleanable Nettoyable - Leicht zu reini	jen - Чист	ящийся				Pulibile - Cleanable Nettoyable - Leicht zu reini;	an - Чистящийся
ź	Resistenza allo scivolamento** - SIp resistance** Résistance au glissement** - Rutshhemmende Eigenschaft** - Conporteurisere скольженио**	DIN 51130 DIN 51097	R9 Matt: - 120x278 - 160x320 - Faro, Comblanchian R10 B Matt WET DCOF >0,42	R11 C Grip WET DCOF	R11 C WET DCOF #0,55						R11 C WET DCOF >0,55	
↓ ↑	Spessore nominale - Nominal Thickness Epaisseur nominal - Nominalistärke - House-anuesa Toruge-a		6 mm 120x278 9 mm 120x120, 60x120, 80x 40x60, 30x60, 20x60	80, 60x60,	20 mm						30 mm	

Manufacturer Details: European Ceramics Approved BPIR COMPLIANT

	<b>120x120 cm</b> 47²/a*x47²/a* 9 mm	<b>80x80 cm</b> 31 <sup>4</sup> /s*x31 <sup>4</sup> /s* 9 mm		<b>60x120 cm</b> 23 <sup>5</sup> /a*x47 <sup>2</sup> /a* 9 mm		<b>60x60 cm</b> 23 <sup>5</sup> /e <sup>*</sup> x23 <sup>5</sup> /e <sup>*</sup> 9 mm	<b>40x60 cm</b> 15%*x23%* 9 mm	<b>30x60 cm</b> 11 <sup>43</sup> /16"x23 <sup>5</sup> /a" 9 mm	20x60 cm 7 <sup>7</sup> /a*x23 <sup>5</sup> /a* 9 mm	<b>10x60 cm</b> 3 <sup>15</sup> /w*x23 <sup>5</sup> /s* 9 mm
	MATTRT	MATT RT	MATT RT	GRIP RT R11 C	GROOVE RT R10 B	MATT RT	MATT RT	MATT RT	MATTRT	MATT RT
Rouen	72		72	Δ		72	72	72	72	72
Erice	72	72	72	Δ		72	72	72	72	72
Faro	•		•	Δ		•	•	•	•	•
Comblanchien	•	•	•	Δ		•	•	•	•	•
Newport	72	72	72	Δ		72	72	72	72	72
Brera	72	72	72	Δ		72	72	72	72	72
Wells	72		72	Δ		72	72	72	72	72
					•	] [				
	120x278 cm 47 <sup>2</sup> /s <sup>*</sup> x109 <sup>2</sup> /s <sup>*</sup> 6 mm MATT RT	<b>160x320 cm</b> 63"xt26" 6 mm <b>MATT RT</b>			<pre></pre>	«47²/»" 23 <sup>5</sup> / mm 2	s"x35 <sup>7</sup> /s" 3 0 mm	30x80 cm 11 <sup>4</sup> /a <sup>+</sup> x3 <sup>4</sup> /a <sup>+</sup> 20 mm	60x60 cm 23 <sup>5</sup> /a"x23 <sup>5</sup> /a" 20 mm	60x60 cm 25 <sup>5</sup> /s <sup>*</sup> x2 <sup>5</sup> /s <sup>*</sup> 30 mm
Erice	47²/s"x109 <sup>7</sup> /s" 6 mm	63"x126" 6 mm		Rouen	<pre></pre>	«47²/»" 23 <sup>5</sup> / mm 2	s"x35 <sup>7</sup> /s" 3 0 mm	20 mm	60x60 cm 23 <sup>5</sup> /a"x23 <sup>5</sup> /a" 20 mm	60x60 cm 23 <sup>5</sup> /a"x23 <sup>5</sup> /a" 30 mm
	47 <sup>2</sup> /s"x109 <sup>7</sup> /s" 6 mm MATT RT	63"x126" 6 mm		Rouen Erice	<pre></pre>	447 <sup>2</sup> /s" 23 <sup>5</sup> / mm 2 0 RT R11 C AEXTR/	a"x357/s" 3 0 mm	20 mm	60x60 cm 23 <sup>5</sup> /s <sup>*</sup> x23 <sup>5</sup> /s <sup>*</sup> 20 mm XTRA20 RT R11 C	60x60 cm 23 <sup>5</sup> /a"x23 <sup>5</sup> /a" 30 mm
Erice Faro Comblanchien	47 <sup>2</sup> /s"x109 <sup>7</sup> /s" 6 mm MATT RT	63"×126" 6 mm MATT RT			× ± ± ± ± ± ± ± ± ± ± ± ± ±	e47°/s" 23°/ mm 2 D RT RH C AEXTR/	a°x35 <sup>7</sup> /a° 3 0 mm A20 RT R11 C AEX	11 <sup>4</sup> /a <sup>-</sup> x31 <sup>4</sup> /a <sup>-</sup> 20 mm TRA20 RT R11 C AE	60x60 cm 23 <sup>5</sup> /a <sup>*</sup> x23 <sup>5</sup> /a <sup>*</sup> 20 mm XTRA20 RT R11 C	60x60 cm 23 <sup>5</sup> /a"x23 <sup>5</sup> /a" 30 mm
Faro	47 <sup>3</sup> /s <sup>*</sup> x109 <sup>3</sup> /s <sup>*</sup> 6 mm MATT RT •	63"×126" 6 mm MATT RT		Erice	× 60x12 × 60x12 × 2201 AEXTRA2	47 <sup>7</sup> /s <sup>-</sup> 23 <sup>4</sup> / mm 2 D RT RH C AEXTR/	*1x35 <sup>7</sup> /** 3 0 mm 3 A20 RT R11 C AEX A	11 <sup>4</sup> /a <sup>-</sup> x31 <sup>4</sup> /a <sup>-</sup> 20 mm TRA20 RT R11 C AE	60x60 cm 23 <sup>5</sup> /s <sup>2</sup> x23 <sup>5</sup> /s <sup>2</sup> 20 mm XTRA20 RT RH C	60x60 cm 23 <sup>5</sup> /a"x23 <sup>5</sup> /a" 30 mm
Faro Comblanchien	47 <sup>2</sup> /s <sup>*</sup> x109 <sup>2</sup> /s <sup>*</sup> 6 mm MATT RT •	63"×126" 6 mm MATT RT		Erice Faro	× 60x12 × 60x14 × 22014 AEXTRA2	0 RT RH C AEXTRU	*1x35 <sup>7</sup> /** 3 0 mm 3 A20 RT R11 C AEX A	TRA20 RT RH C AE	60x60 cm 23%/s/23%/s 20 mm XTRA20 RT Rti C A	60x60 cm 23 <sup>5</sup> /a"x23 <sup>5</sup> /a" 30 mm
Faro Comblanchien Newport	47 <sup>9</sup> /sx109 <sup>9</sup> /s <sup>4</sup> 6 mm MATT RT • •	63"×126" 6 mm MATT RT		Erice Faro Comblanchi	× 60×12 × 60×12 × 220 AEXTRA2	0 RT RH C AEXTRU	1°335//«* 3 0 mm A20 RT R1 C AEX	A A A A A A A A A A A A A A A A A A A	60x60 cm 225%25% 20 mm XTRA20 RT RH C A	60x60 cm 23 <sup>5</sup> /a"x23 <sup>5</sup> /a" 30 mm
Faro Comblanchien Newport	47%x109%* 6 mm • •	63"×126" 6 mm MATT RT		Erice Faro Comblanchi Newport	× 60×12 × 60×12 × 220 AEXTRA2	ATFIS" 234/ mm 2 D RT RH C AEXTRU	1°335//«* 3 0 mm A20 RT R1 C AEX	A A A A A A A A A A A A A A A A A A A	60x60 cm 223//s <sup>1</sup> /223//s <sup>2</sup> 20 mm XTRA20 RT RH C A A A	60x60 cm 23 <sup>5</sup> /a"x23 <sup>5</sup> /a" 30 mm

Manufacturer Details: European Ceramics Approved BPIR COMPLIANT

### Fire Resistance

The building code relating to fire rating regulations and standards requires specifiers to provide documentation such as fire certificates for materials used in construction.

Ceramics are in itself a fire-resistant material, mostly being manufactured at over 1200 degrees Celsius. Testing and providing such certification are therefore not relevant to the Ceramics industry.

Ceramic and Porcelain tiles are an inert material, and therefore non-combustible. They do not release fumes or toxic gases in the event of a fire. Porcelain tiles contain no sealants, waxes or other chemicals that could release VOC's into the environment. Ceramics do not pose a risk of spreading or intensifying a fire therefore there is no testing required as they do not contribute to a fire.

EXTRAORDINARY EFFECTS DURING USE PHASE:

Fire: According to /EN 13501-1:2007+A1:2009/, ceramic tiles can be classified as A1 class of fire resistance rating, because they do not contribute to fire.

It has been demonstrated that the coating of the ceramic tiles, in case of fire, reduces heat on them and thus the risk of collapse.

Water: Ceramic tiles cannot react with water because they are an insoluble material.

For further information on the physio-characteristics of fire resistance for tiles please refer to the Technical Documents section on euroceramics.co.nz

Manufacturer Details: European Ceramics Approved BPIR COMPLIANT